

Name of the Material : Wood Pellet Powder

Material Code : UME BIOFMET CRM 02

Issue Date : 27.12.2024

Revision Date : 27.12.2024 (Revision history can be found on the last page)

Validity Period of the Certificate : 12 months from the sales date

Certified Values :

Parameter	Certified Value ^[1]	Uncertainty ^[2]	Unit
Gross Calorific Value [$q_{V,gr,d}$] ^[3]	20690	136	J/g
Moisture ^[4]	7.30	0.34	g/100 g
Ash ^[5]	0.231	0.040	g/100 g
Al ^[6]	16.5	1.9	mg/kg
Cr ^[7]	7.40	0.85	mg/kg

- [1] The certified values and uncertainties are traceable to the International System of Units (SI). Certified values are corrected for dry mass except the moisture parameter. Moisture content is determined at (105 ± 2) °C until constant weight as defined in ISO 18134-3 method.
- [2] The expanded uncertainty of the certified value includes characterization, homogeneity, stability components and is stated as the standard uncertainty of measurement multiplied by the coverage factor $k = 2$, which for a normal distribution corresponds to a coverage probability of approximately 95 %. The standard uncertainty of measurement has been determined in accordance with GUM "Guide to the Expression of Uncertainty in Measurement".
- [3] Calculated from the arithmetic mean of the accepted results of the gross calorific value at constant volume of the dry fuel submitted by four laboratories applying ISO EN 18125 method.
- [4] Calculated from the arithmetic mean of the accepted results submitted by two laboratories applying ISO 18134-3 method.
- [5] Calculated from the arithmetic mean of the accepted results submitted by two laboratories applying ISO 18122 method.
- [6] Calculated from the arithmetic mean of the accepted results submitted by two laboratories applying ICP-MS and MPAES methods.
- [7] Calculated from the arithmetic mean of the accepted results submitted by three laboratories applying ICP-MS, HR ICP-MS and MPAES methods.

Sales Date


Assoc. Prof. Mustafa ÇETİNTAŞ
Acting Director

The following pages are an integral part of the certificate. The use of current certificate is customers' responsibility.

Most recent certificate can be downloaded from www.ume.tubitak.gov.tr

Certified Values (continued) :

Parameter	Certified Value ^[1]	Uncertainty ^[2]	Unit
K ^[6]	317	60	mg/kg
Mg ^[6]	166	42	mg/kg
Mn ^[6]	74.3	7.4	mg/kg
Ni ^[8]	5.92	0.77	mg/kg
S ^[9]	68.3	9.5	mg/kg
Zn ^[8]	8.5	1.2	mg/kg

- [1] The certified values and uncertainties are traceable to the International System of Units (SI). Certified values are corrected for dry mass. Moisture content is determined at (105 ± 2) °C until constant weight as defined in ISO 18134-3 method.
- [2] The expanded uncertainty of the certified value includes characterization, homogeneity, stability components and is stated as the standard uncertainty of measurement multiplied by the coverage factor $k = 2$, which for a normal distribution corresponds to a coverage probability of approximately 95 %. The standard uncertainty of measurement has been determined in accordance with GUM "Guide to the Expression of Uncertainty in Measurement".
- [6] Calculated from the arithmetic mean of the accepted results submitted by two laboratories applying ICP-MS and MPAES methods. Calculated from the arithmetic mean of the accepted results submitted by four laboratories applying ICP-MS, HR ICP-MS and MPAES methods.
- [8] Calculated from the arithmetic mean of the accepted results submitted by four laboratories applying ICP-MS, HR ICP-MS and MPAES methods.
- [9] Calculated from the arithmetic mean of the accepted results submitted by four laboratories applying ICP-MS, HR ICP-MS and ID ICP-MS methods.

Informative Values

Parameter	Assigned Value	Uncertainty ^[1]	Unit
Net Calorific Value $[q_{V,net,m}]$ ^[2]	17992	119	J/g
As ^[3]	0.55	0.33	mg/kg
Ca ^[4]	674	177	mg/kg
Cd ^[3]	0.25	0.11	mg/kg
Cu ^[5]	0.55	0.18	mg/kg
Fe ^[4]	9.7	2.9	mg/kg
Hg ^[3]	0.27	0.13	mg/kg
Na ^[4]	27	14	mg/kg
P ^[6]	77	24	mg/kg
Pb ^[5]	4.4	1.3	mg/kg

- [1] The expanded uncertainty of the assigned value includes characterization, homogeneity, stability components and is stated as the standard uncertainty of measurement multiplied by the coverage factor $k = 2$, which for a normal distribution corresponds to a coverage probability of approximately 95 %. The standard uncertainty of measurement has been determined in accordance with GUM "Guide to the Expression of Uncertainty in Measurement".
- [2] Calculated for as received moisture from the certified gross calorific value at constant volume of dry fuel using the following equation: $q_{V,net,m} = [q_{V,gr,d} - 206 \times \text{hydrogen content of moisture free biofuel, in percentage by mass}] \times (1 - 0.01 \times \text{moisture, in percentage by mass}) - (23.0 \times \text{moisture, in percentage by mass})$ as described in ISO 18125.
- [3] Calculated from the arithmetic mean of the accepted results submitted by two laboratories applying ICP-MS and HR ICP-MS methods.
- [4] Calculated from the arithmetic mean of the accepted results submitted by two laboratories applying ICP-MS and MPAES methods.
- [5] Calculated from the arithmetic mean of the accepted results submitted by four laboratories applying ICP-MS, HR ICP-MS and MPAES methods.
- [6] Calculated from the arithmetic mean of the accepted results submitted by one laboratory applying ICP-MS method.

The use of current certificate is customers' responsibility. Most recent certificate can be downloaded from www.ume.tubitak.gov.tr

Element	Measured Value ^[1]	SD ^[2]	Unit
C	50.35	0.38	g/100 g
H	5.34	0.10	g/100 g
N	0.330	0.034	g/100 g

[1] Arithmetic mean of the accepted analysis results (n = 12) by one laboratory applying ISO 16948 method.

[2] Standard deviation of the 12 measurement results.

Description

The material is approximately 50 g of wood pellet powder in amber glass bottle. Detailed information about the preparation of the material can be found in the certification report.

Intended Use

This material is intended to be used for method validation of the determination of calorific value, moisture, ash and mass fractions of Al, Cr, K, Mg, Mn, Ni, S and Zn elements in wood products and for quality control purposes.

Instructions for Use

Bottle should be shaken before opening the cap. In order to prevent contamination, it is recommended that the bottle should be opened in a clean environment. After use, the bottle should be tightly recapped immediately.

The minimum sample intake is defined by the required sample mass stipulated in the respective standard methods.

For elemental analysis, during the measurements performed for homogeneity, characterization, stability studies, the lowest amount used was 0.2 g and no sign of heterogeneity have been observed. Therefore, this can be considered as the minimum sample amount to be used in the elemental analysis.

It should be noted that the moisture content of the materials can decrease or increase after several use depending on the relative humidity (RH) of the laboratory. For moisture analysis, it is recommended to open the bottle cap under (50 ± 5) %rh condition and/or close it as quick as possible to minimize moisture change.

This material can be safely dispatched under conditions where the temperature does not exceed 45 °C for up to two weeks, i.e. at ambient temperature without applying any cooling elements.

Storage Conditions

The material should be stored at (22 ± 4) °C in a dark and clean environment. TÜBİTAK UME cannot be held responsible for changes that might happen to the material at the customer's premises due to non-compliance with the instructions for use, and the storage conditions given.

Safety Information

For laboratory use only. The usual laboratory safety measures apply as in the case of similar powders. It is strongly recommended that the material must be handled and disposed according to the safety guidelines where applicable. It is recommended to avoid inhalation of powder material and work under appropriate ventilation conditions. No special precaution is necessary to work with the wood pellet material.

Participants

Information about the laboratories participated in the characterization study is presented in the following table.

Laboratory	Address
BAM	Bundesanstalt für Materialforschung und -prüfung, Berlin, GERMANY
BRML-INM	BRML-INM, National Metrology Institute, Bucharest, ROMANIA
DTI	Danish Technological Institute, Aarhus, DENMARK
GUM	Central Office of Measures, Warszawa, POLAND
IMBiH	Institute of Metrology of Bosnia & Herzegovina, Sarajevo, BOSNIA and HERZEGOVINA
PTB	Physikalisch Technische Bundesanstalt, Braunschweig, GERMANY
TÜBİTAK UME	National Metrology Institute, Gebze - Kocaeli, TÜRKİYE

Methods and/or Techniques Used for the Determination of the Certified Values

Techniques used in the characterization studies:

Method/Technique	Parameter
ISO EN 18125 / Isoperibol Calorimetry	Calorific Value
ISO 18134-3 / Oven Drying based on gravimetry	Moisture
ISO 18122 / Ash Analysis based on gravimetry	Ash
Inductively Coupled Plasma Mass Spectrometry (ICP-MS)	Al, Cr, K, Mg, Mn, Ni, S, Zn
High Resolution Inductively Coupled Plasma Mass Spectrometry (HR ICP-MS)	Cr, Ni, S, Zn
Microwave Plasma Atomic Emission Spectroscopy (MPAES)	Al, Cr, K, Mg, Mn, Ni, Zn
Isotope Dilution Inductively Coupled Plasma Mass Spectrometry (ID-ICP-MS)	S

Revision History

Date	Remarks
27.12.2024	First issue.